

AD612897

AD

TECHNICAL REPORT ECOM-2553

DIELECTRIC CONSTANT OF GERMANIUM AS A FUNCTION
OF FREQUENCY, TEMPERATURE, AND RESISTIVITY

BY


MAURICE A. DRUESNE

JANUARY 1965

ECOM

UNITED STATES ARMY ELECTRONICS COMMAND • FORT MONMOUTH, N.J.

COPY	7	OF	3	18
HARD COPY			\$.	1.00
MICROFICHE			\$.	0.50



ARCHIVE COPY

DDC AVAILABILITY NOTICE

Qualified requesters may obtain copies of this report from Defense Documentation Center, Cameron Station, Alexandria, Virginia 22314.

This report has been released to the Clearinghouse for Federal Scientific and Technical Information, U. S. Department of Commerce, Springfield, Virginia 22151, for sale to the general public.

Disclaimer

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Disposition

Destroy this report when it is no longer needed. Do not return it to the originator.

Address Change

In case of a change in address, the recipient of this report should notify U. S. Army Electronics Command, Attn: AMSEL-IO-T, Fort Monmouth, N. J.

DIELECTRIC CONSTANT OF GERMANIUM AS A FUNCTION
OF FREQUENCY, TEMPERATURE, AND RESISTIVITY

by

Maurice A. Druesne

Solid State and Frequency Control Division
Electronic Components Department

January 1965

DA Task Nr. 1P6-22001-A-056-03-22

U. S. ARMY ELECTRONICS LABORATORIES
U. S. ARMY ELECTRONICS COMMAND
FORT MONMOUTH, NEW JERSEY

Abstract

The use of semiconductors in electronics has increased tremendously during the last decade and this growth will continue. One of the most important characteristics of semiconductors is the dielectric constant which determines their electrical behavior.

Measurements of the dielectric constant have been made on p- and n-type germanium of various resistivities (20, 10, and $1/2$ ohm-cm). At the same time the dielectric constant has been found to decrease with lower temperatures down to 78°K.

Similarly, the dielectric constant has been measured at various frequencies and was found to decrease with increasing frequency. At very low resistivity ($1/2$ ohm-cm) some anomalous behavior is found which is due to the fact that the material is no longer really a semiconductor, but begins to act as a conductor.

CONTENTS

	<u>Page</u>
Abstract	
INTRODUCTION	1
MEASUREMENT TECHNIQUE	1
RESULTS	2
CONCLUSIONS	3
REFERENCES	4

FIGURES

1. Microwave Setup for Dielectric Constant Measurements	5
2. Dielectric Constant of Germanium (P Type 20 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	6
3. Dielectric Constant of Germanium (P Type 10 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	7
4. Dielectric Constant of Germanium (P Type 1/2 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	8
5. Dielectric Constant of Germanium (N Type 20 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	9
6. Dielectric Constant of Germanium (N Type 10 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	10
7. Dielectric Constant of Germanium (N Type 1/2 ohm-cm) as a Function of Temperature at 61.3 and 92 Gc	11

DIELECTRIC CONSTANT OF GERMANIUM AS A FUNCTION OF FREQUENCY, TEMPERATURE, AND RESISTIVITY

INTRODUCTION

The dielectric constant constitutes an important characteristic of a semiconductor, and affects the static and dynamic properties of devices utilizing it.

The dielectric constant of germanium has been measured by many authors at various frequencies and temperatures, and for a variety of reasons. Benedict and Shockley,¹ for instance, measured it at 1.24 cm for their determination of the effective mass. Goldey and Brown² repeated the measurements at 24 Gc to check the value of the effective mass. D'Altroy et al,^{3,4} have also published results on germanium at 9.2 Gc and low-temperatures in their study of the effect of neutral impurities.

Recently, bulk effects in semiconductors have come to the fore in such applications as maser, laser, hot-carrier thermoelectric effect, phonon parametric amplifier, etc. In these new effects the characteristics of the bulk material become paramount, and some of these effects are utilized at higher frequencies than those for which dielectric measurements have previously been carried out. The present work on dielectric measurement fulfills a current need in measuring the behavior of the bulk dielectric constant more systematically as a function of temperature, frequency, and resistivity at millimeter frequencies. Values are given for arsenic doped n-type and gallium p-type germanium.

MEASUREMENT TECHNIQUE

The measurement of the dielectric constant was carried out at microwave frequency by making use of the standing wave pattern technique. The introduction of the sample into the waveguide produces a change in the standing wave, and this change is the basis for the calculation of the dielectric constant. The theory of this method was established by Roberts and Von Hippel,⁵ and by Westphal.⁶

The reduction of the data leads to a complex transcendental equation:

$$\angle \psi = \frac{\text{Tanh}(T \angle \tilde{\epsilon})}{T \angle \tilde{\epsilon}} \quad (1)$$

that must be solved for T and $\tilde{\epsilon}$. This can be done by programming a computer or by making use of extensive charts published in the literature, and particularly by Westphal.⁶ A much simpler approximate solution to this equation can be readily obtained. The dielectric material in the waveguide can be viewed as a four-terminal structure, and the dielectric constant is then obtained from the determinant of the admittance representation. In this method, however, a great many variations in detail are possible. The particular method adopted consisted of placing the sample right against the moving plunger of the sliding short used to create the standing wave pattern. The sample itself is cut and ground to fit the waveguide exactly. This method provides the advantage of allowing operation of the microwave system in a vertical position which is advantageous for cooling the sample to 78°K by immersion of the sliding short into a dewar containing liquid nitrogen.

Conversely to measure at +60°C, the sliding short is placed over a small electric heater.

The measurements at high microwave frequencies (61.3 and 92 Gc) are difficult to carry out due to the increased instability of the microwave sources. Klystrons, at these frequencies, tend to drift and the power available (of the order of 60 to 70 mw) is barely enough due to the high attenuation in the waveguide system.

At low temperatures, condensation may occur inside the waveguide and thus cause erroneous results. Finally, the length of the sample becomes extremely critical, especially at low resistivities, and a great many readings are required to insure accuracy. A block diagram of the experimental arrangement is shown in Fig. 1.

RESULTS

Dielectric measurements were made on both n- and p-type germanium having the following approximate dc resistivities: 1/2, 10, and 20 ohm-cm. The actual resistivities were as follows:

n-type germanium - 0.563, 11.03, and 17.33 ohm-cm

p-type germanium - 0.315, 12.41, and 18.91 ohm-cm.

All samples were measured at frequencies of 61.3 and 92 Gc, and at four different temperatures ranging from liquid nitrogen to +60°C. The results of all the measurements are plotted in Fig. 2-7 as the dielectric constant as a function of the temperature for the two frequencies 61.2 and 92 Gc.

The following conclusions are noted:

1. For both n- and p-type germanium of 20 and 10 ohm-cm resistivities, the dielectric constant decreases as the temperature decreases, as shown in Fig. 2, 3, 5, and 6.
2. For both n- and p-type germanium of 1/2, 10, and 20 ohm-cm resistivities, the dielectric constant decreases as the frequency increases, as shown in Fig. 2-7.
3. For the p-type germanium of 1/2 ohm-cm resistivity, the dielectric constant decreases as the temperature decreases at 61.3 Gc, but at 92 Gc it remains nearly constant with the temperature, as shown in Fig. 4.
4. For the n-type germanium of 1/2 ohm-cm resistivity, the dielectric constant decreases as the temperature decreases at 61.3 Gc, but at 92 Gc it increases as the temperature decreases, as shown in Fig. 7.

The standard deviation was calculated for groups of readings leading to results shown on the curves, and it varied from a low of $\sigma = 0.15$ to a high of $\sigma = 0.29$. The results are, therefore, in doubt at most by ± 0.30 . The results presented are based upon one sample of each type and resistivity. More reliable data would be obtained if several samples had been put through the two frequencies and the various temperatures. Unfortunately, only one ingot of each type and resistivity was available, thus limiting the data obtained.

Finally, it may seem that the knee in the various curves is arbitrarily located. To a certain extent it may be so, but in three cases a temperature of about -110°C is reached before the dielectric constant begins to decrease. On the strength of this fact the knee of the other curve is placed below that temperature thus assuming that the various samples would behave identically (except the n- and p-type of germanium of $1/2$ ohm-cm at 92 Gc).

CONCLUSIONS

Both n- and p-type germanium of $1/2$ ohm-cm resistivities behave anomalously at 92 Gc as a function of the temperature. The measurements were carefully checked and appear beyond doubt.

In order to explain the behavior of the dielectric constant as a function of temperature and frequency, an attempt was made to calculate the values theoretically. At high frequencies the dielectric constant is given by

$$k(\omega) = k_0 + \frac{4\pi}{\omega} \sigma_1 \quad (2)$$

where:

k_0 = dc values of the dielectric constant

ω = angular frequency

σ_1 = imaginary term of the conductivity as given by:

$$\sigma(\omega) = \sigma_r + i \sigma_1 \quad (3)$$

where:

$\sigma(\omega)$ = conductivity at angular frequency ω

σ_r = real term of conductivity.

At microwave frequencies, therefore, the dielectric constant is a function of the conductivity and this, in turn, is a function of the mobility.

When the frequency reaches a certain value, the carriers can no longer follow the field, the conductivity decreases and so does the dielectric constant. The theoretical study of the dielectric constant as a function of frequency and resistivity is essentially a study of the mobility of the carriers.

The simplest method, and the one tried first, was to assume spherical energy surfaces for a non-degenerate semiconductor. The approach consists of calculating the electrical conductivity on the basis of combining the two scattering mechanisms resulting from the lattice and the impurities.

The neutral impurity scattering was neglected since the temperature was only 78°K.⁷ The two scattering mechanisms can be considered as being independent, and the effective mean free path is given by:

$$\frac{1}{l} = \frac{1}{l_t} + \frac{1}{l_i} \quad (4)$$

where:

l_t = mean free path due to thermal (lattice) scattering

l_i = mean free path due to impurity scattering, some uncertainty attaches to this value of the effective mean free path since it depends upon the value of the effective mass which is itself in doubt.


Because of the assumptions made and of the uncertainties involved in the quantities used, this simple theory based on spherical energy surfaces does not yield a satisfactory agreement with the experimental results.

A more sophisticated approach involves the use of the so-called many valley theory⁸ where the energy surfaces are ellipsoids for the non-degenerate semiconductor. But even with the more realistic approach, the results of the experiments and of the calculations still do not agree.

The conclusions to be reached from these attempts is that the present theories of mobilities are inadequate to account for the behavior of the dielectric constant even for high resistivities, let alone the anomalous behavior of the 1/2 ohm-cm resistivity n- and p-type germanium. More experiments and theoretical work are required, especially at low resistivities and millimeter waves.

REFERENCES

1. T. S. Benedict and W. Shockley, Phys. Rev. 89, 1152 (1955).
2. J. M. Goldey and S. C. Brown, Phys. Rev. 98, 1761 (1955).
3. F. A. D'Altroy and H. Y. Fan, Phys. Rev. 100, 1260 (1955).
4. F. A. D'Altroy and H. Y. Fan, Phys. Rev. 103, 1671 (1956).
5. S. Roberts and A. Von Hippel, J. Appl. Phys. 17, 610 (1946).
6. W. B. Westphal et al, Tech. Rpt. XXXVI, Laboratory for Insulation Research, M. I. T. July 1950.
7. P. P. Debye and E. M. Conwell, Phys. Rev. 93, 693 (1954).
8. C. Herring, Bell System Tech. J. 34, 237 (1955).



FXR Z815B




FIGURE 1
MICROWAVE SET-UP FOR DIELECTRIC CONSTANT
MEASUREMENTS




FIGURE 2
DIELECTRIC CONSTANT OF GERMANIUM (P TYPE 20 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc




FIGURE 3
DIELECTRIC CONSTANT OF GERMANIUM (P TYPE 10 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc




FIGURE 4
DIELECTRIC CONSTANT OF GERMANIUM (P TYPE 1/2 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc




FIGURE 5
DIELECTRIC CONSTANT OF GERMANIUM (N TYPE 20 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc




FIGURE 6
DIELECTRIC CONSTANT OF GERMANIUM (N TYPE 10 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc




FIGURE 7
DIELECTRIC CONSTANT OF GERMANIUM (N TYPE 1/2 OHM-CM)
AS A FUNCTION OF TEMPERATURE AT 61.3 AND 92 Gc

BLANK PAGE

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1 ORIGINATING ACTIVITY (Corporate author) U. S. Army Electronics Command Fort Monmouth, N. J.		2a REPORT SECURITY CLASSIFICATION UNCLASSIFIED	
		2b GROUP	
3 REPORT TITLE DIELECTRIC CONSTANT OF GERMANIUM AS A FUNCTION OF FREQUENCY, TEMPERATURE, AND RESISTIVITY			
4 DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Report			
5 AUTHOR(S) (Last name, first name, initial) Druesne, Maurice A.			
6 REPORT DATE January 1965		7a TOTAL NO. OF PAGES 11	7b NO. OF REFS 8
8a CONTRACT OR GRANT NO.		9a ORIGINATOR'S REPORT NUMBER(S) ECOM-2553	
b. PROJECT NO. 1P6-22001A056			
c. Task No. -03		9b OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d. Subtask No. -22			
10 AVAILABILITY LIMITATION NOTICES QUALIFIED REQUESTORS MAY OBTAIN COPIES OF THIS REPORT FROM DDC. THIS REPORT HAS BEEN RELEASED TO THE CFSTI, DEPT OF COMMERCE.			
11 SUPPLEMENTARY NOTES Behavior of dielectric constant in semiconductors.		12 SPONSORING MILITARY ACTIVITY U. S. Army Electronics Labs., AMSEL-RD-PFM U. S. Army Electronics Command Fort Monmouth, N. J. 07703	
13 ABSTRACT The use of semiconductors in electronics has increased tremendously during the last decade and this growth will continue. One of the most important characteristics of semiconductors is the dielectric constant which determines their electrical behavior. Measurements of the dielectric constant have been made on p- and n-type germanium of various resistivities (20, 10, and 1/2 ohm-cm). At the same time the dielectric constant has been found to decrease with lower temperatures down to 78°K. Similarly, the dielectric constant has been measured at various frequencies and was found to decrease with increasing frequency. At very low resistivity (1/2 ohm-cm) some anomalous behavior is found which is due to the fact that the material is no longer really a semiconductor, but begins to act as a conductor. (Author)			

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Solid State Physics Electricity and Magnetism Physical and Physico-Chemical Concepts Plasma Physics Atomic and Molecular Physics Quantum Theory Crystallography Electromagnetic Wave Phenomena						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (*corporate author*) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (*either by the originator or by the sponsor*), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (*paying for*) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

BLANK PAGE